



FEATURES AND BENEFITS

- Recycled REPREVE® Polyester
- Eco-Friendly
- Full Coverage
- Free Cut
- Moisture Wicking
- UPF 50+
- High Performance
- Support
- Great Shape and Retention
- Peached finish

SUGGESTED APPLICATIONS

- Active Sports
- Swimwear
- Dancewear

ECO PLATINUM PEACHED

Recycled ECO PLATINUM PEACHED has been developed using REPREVE® yarn, the leading branded performance fiber made from recycled single use plastic bottles that were destined for landfill.

Knitted with a high performance end use in mind, the unique structure gives you a full coverage, free cut fabric with fantastic support, shape and retention along with an additional soft peached finish.

With the added benefits of a Moisture Wicking finish and UPF 50+ rating, ECO PLATINUM is at the forefront of innovation for performance and sustainability.

Global Recycled Standard and OKEO-TEX 100 certified, the REPREVE® Polyester yarn is one of the most certified, traceable fibers available in the world.

[Request a sample >](#)



Fiber made from recycled plastic bottles...to do good.

Pre-consumer fiber waste and post-consumer plastics are collected.

The collected waste then enters a unique material conversion process where it is chopped, ground, melted, and reformulated.

Recycled resin is formed.



REPREVE® POLYESTER

The chip is extruded and textured through a proprietary process.

PRODUCT SPECIFICATIONS

Composition:
75% Recycled REPREVE® Polyester
25% Elastane

Weight:
260gsm +/- 5%

Width:
150cm +/- 5%

Email: eclipse@eclipsetextiles.com.au

Phone: +61 7 3251 2970

Fax: +61 7 3251 2971



www.eclipsetextiles.com.au

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values of Washing, Water and Sea Water are lower than 4/5. When splicing colours with white we also recommend using Polyester LYCRA®.

COLOUR	LIGHT AS2001.4.21 60HRS			RUBBING AS2001.4.3				WASHING 40oc AS2001.4.15 TEST J2				WATER AS2001.4-E01				PERSPIRATION AS2001.4-E04			
	C.C	Dry	Wet	C.C	S.Co	S.Pa	S.PI	C.C	S.Co	S.Pa	S.PI	C.C	S.Co	S.Pa	S.PI				
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A				
BLACK	3-4	4	4	4-5	4	3-4	3-4	4-5	3-4	3-4	4	4-5	4	3-4	4				

C.C. = Colour Change. S.Co = Staining on Cotton. S.Pa = Staining on Nylon. S.PI = Staining on Polyester.

Relaxation of up to 5% is to be expected on all Elastane-based fabrics and is not claimable on Eclipse Textiles. 5% relaxation allowance should be calculated into stock requirement figures.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		

