



FEATURES AND BENEFITS

- ISO 50001:2018 Energy Management Systems Certified
- OEKOTEX® 100 Certified
- Breathable
- Moisture wicking
- Soft natural handle
- Faster drying than cotton
- Easy care and crease resistant
- Shape retention
- Maximum durability
- Branded LYCRA®

SUGGESTED APPLICATIONS

- Performance sports wear
- Yoga wear
- Dance costumes
- Gymnastic leotards
- Fashion and intimate apparel

EMPOWER SUPPLEX® LYCRA® HEAVY WEIGHT

High quality Supplex® LYCRA® stocked in a number of on trend colours. Superior natural Cotton handle due to the use of jet air textured Nylon yarn. Features like breathability and faster drying than Cotton, make Supplex® the ideal choice for a supportive active sports garment.

Combined with the higher LYCRA® content, the heavier weight gives you support, shape and retention which is an essential requirement for the sports industry.

PRODUCT SPECIFICATIONS:

Composition:
86% Supplex®, 14% LYCRA®

Weight:
280gsm +/- 5%

Width:
150cm +/- 5%

[Request a sample >](#)

OEKOTEX® STANDARD 100 CERTIFIED

The OEKO-TEX® Standard 100 is a globally uniform testing and certification system for textile raw materials, intermediate and end products at all stages of production. Its aim is to ensure products are free of harmful substances.

COMPLEMENTING FABRICS

[Sports Fabric Breathable EMPOWER SUPPLEX® LYCRA®](#)

COLOUR FASTNESS VALUES

PLEASE PAY SPECIAL ATTENTION to the fastness values declared in the chart:
Combination of colours is not recommended when the fastness values of Washing, Water and Sea Water are lower than 4/5.

C.C. = Colour Change.
S.Pa = Staining on Nylon.
S.PI = Staining on Polyester.
S.Co = Staining on Cotton.

| COLOUR FASTNESS ASSESSMENT VALUES | | | |
|-----------------------------------|-------------|-------------|-------------|
| LIGHT | ASSESSMENTS | OTHER TESTS | ASSESSMENTS |
| 1 | Very Weak | 1 | Weak |
| 2 | Weak | 2 | Limited |
| 3 | Moderate | 3 | Fair |
| 4 | Fair | 4 | Good |
| 5 | Good | 5 | Very Good |
| 6 | Very Good | | |
| 7 | Optimal | | |
| 8 | Exceptional | | |

| COLOUR | LIGHT AS2001.4.21 60HRS | RUBBING AS2001.4.3 | | WASHING 40 °C AS2001.4.15 | | | | WATER AS2001.4-E01 | | | PERSPIRATION AS2001.4-E04 | | | | |
|------------|-------------------------------|-----------------------|-----|------------------------------|------|------|-----|-----------------------|------|------|------------------------------|------|------|------|-----|
| | C.C | Dry | Wet | S.Co | S.Pa | S.PI | C.C | S.Co | S.Pa | S.PI | C.C | S.Co | S.Pa | S.PI | C.C |
| VERY BLACK | 5-6 | 4-5 | 4-5 | 4-5 | 4 | 4-5 | 4-5 | 4.5 | 4 | 4-5 | 4-5 | 4-5 | 4 | 4-5 | 4-5 |